

Our Ref: SW/LS/BR

16 January 2019

**Report 335638**

**Page 1 of 3**

Camira Fabrics Limited  
Meltham Mills  
Meltham  
Huddersfield  
West Yorkshire  
HD9 4AY

Contact: Katy Longstaff;Greta Ziaugraite

DATE RECEIVED : 9 JAN 2019  
 QUALITY/REFERENCE : HALYCON CEDAR  
 REPUTED FIBRE CONTENT : NOT GIVEN  
 FABRIC DESCRIPTION : WOVEN  
 COLOUR/DESIGN : PETAL (HHPC01)  
 ORDER NUMBER : 83A02264

PERFORMANCE STANDARD : GENERAL



**REPORT SUMMARY**

Tests	Method	Pass	Fail	Requirement
Hydrostatic head	Hydrostatic Head BS 3424-26:1990 Method 29A			No requirement




**S. WISEMAN**  
**LABORATORY DIRECTOR**

**L. SHERIDAN**  
**LABORATORY MANAGER**



118 Lupton Avenue Leeds LS9 6ED  
 Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk  
 Registered No. 2899980 VAT No. 613 4310 86

16 January 2019

**Report 335638**

**Page 2 of 3**

*This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.*



118 Lupton Avenue Leeds LS9 6ED  
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: [hstts@hstts.co.uk](mailto:hstts@hstts.co.uk)  
Registered No. 2899980 VAT No. 613 4310 86

16 January 2019

**Report 335638**

**Page 3 of 3**

**PHYSICAL**

**Hydrostatic Head BS 3424-26:1990 Method 29A**

Sample area	100cm <sup>2</sup>
Test atmosphere	20°C 65% R.H
Water temperature	20°C
Rate of rise of water pressure	60cm/1min

Test 1	321 cms/H <sub>2</sub> O * Coating Delaminated
Test 2	344 cms/H <sub>2</sub> O * Coating Delaminated
Test 3	328 cms/H <sub>2</sub> O * Coating Delaminated
Test 4	252 cms/H <sub>2</sub> O * Coating Delaminated
Test 5	394 cms/H <sub>2</sub> O * Coating Delaminated

Requirement:

---

