

Our Ref: SW/MG/BR

7 January 2014

Report 208686/2

Page 1 of 2

Camira
Hopton Mills
Mirfield
West Yorkshire
WF14 8HE

Contact: Daniel Young

DATE RECEIVED	: 9 OCT 2013
QUALITY/REFERENCE	: INTERVENE TEXTURE
REPUTED FIBRE CONTENT	: NOT GIVEN
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: BLUE
STYLE NUMBER	: 1826
END USE	: CONTRACT UPHOLSTER
ORDER NUMBER	: 45930
PERFORMANCE STANDARD	: GENERAL

REQUEST: Hydrostatic head



S. WISEMAN
LABORATORY DIRECTOR

M. GRAINGER
SENIOR TECHNOLOGIST

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.



7 January 2014

Report 208686/2

Page 2 of 2

PHYSICAL

BS 3424 PART 26 METHOD 29A

Sample area	100cm ²
Test atmosphere	20°C 65% R.H
Water temperature	20°C
Rate of rise of water pressure	60cm/1min

Test 1	228 cms/H ₂ O
Test 2	221 cms/H ₂ O
Test 3	214 cms/H ₂ O
Test 4	207 cms/H ₂ O
Test 5	223 cms/H ₂ O
Mean	218.6 cms/H ₂ O

* All samples delaminated and burst

