

Confidential Report

Our Ref: 23/61895/03/24







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 21 March 2024

Our Ref: 23/61895/03/24 Your Ref: 83A26448

Page: 1 of 5

Client: Camira Fabrics Ltd

The Watermill Wheatley Park Mirfield West Yorkshire WF14 8HE

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: 83A26448

Date of Receipt: 13 March 2024

Date Test Started: 21 March 2024

Description of Sample: One sample of fabric, which was referenced by the client as;

Main Line Flax / Main Line Twist / Monochrome Sett

Batch: 517458, Colour: Crimp

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 8

subcontracted test, UKAS accredited

** subcontracted test, EN ISO/IEC 17025 accredited

*** not UKAS accredited





1066

Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 21 March 2024

Our Ref: 23/61895/03/24 Your Ref: 83A26448

Page: 2 of 5

Client: Camira Fabrics Ltd

Product Description

Company Name	Camira Fabrics	
FABRIC		
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	Upholstery Fabric	
Name and/or Identification of the Product Tested	Mail Line Flax / Main Line Twist / Monochrome Sett	
Materials of the product and its Composite Ratio (i)	75% Wool, 25% Flax	
Composition of Weave (ii)	Plain Weave	
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	IP	
Yarn Number Count	IP	
Thickness (mm)	1.4 mm (nominal)	
Mass per Unit Area (g/m²)	437 g/m2	
Colour and Tone (iii)	Crimp MLT06	
Method and Quantity of Fire Retardant Treatment (type and amount per m²)	None	
FILLINGS (if applicable)		
Material (Name of the Manufacturer, Type Designation);	N/A	
Weight per Unit Volume (kg/m³)	N/A	
Method and Quantity of Fire Retardant Treatment (type and amount)	N/A	

- (i) Such as wool, nylon, polyester, etc.
- Such as plain, weave, twilled.
- If the product has a pattern, the representative colour shall be described.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 21 March 2024

Our Ref: 23/61895/03/24 Your Ref: 83A26448

> Page: 3 of 5

Client: **Camira Fabrics Ltd**

Testing to IMO FTP Code 2010: Part 8

Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 23±2°C temperature and 50±5% relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m³ and 19°C.

Procedure

The samples was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22kg/m³.

Requirements

No progressive smouldering or flaming within 1 hour of the placement of the cigarette. Ignition Source 0

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm) 69mm x 8.0mm

Mass (g) 0.93 Smouldering Rate (mins/secs) 9m 58s







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 21 March 2024

Our Ref: 23/61895/03/24 Your Ref: 83A26448

> Page: 4 of 5

Client: Camira Fabrics Ltd

Results

Cigarette Test - Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	DNP	DNP
Time of cover split	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Observations	DNP/DNS	DNP/DNS
Pass/Fail	PASS	PASS

Result of the Cigarette Test: Pass

Propane Flame Test – Source 1

Specimen No.	1	2
Time of Ignition (s)	5	6
Extinction time of flames after removal of burner (s)	1	1
Time to Cover Split (s)	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Observations:	DNS	DNS
Pass/Fail	PASS	PASS

Result of the Flame Test: Pass

Acronym

DNP – Did not propagate ES - Escalating smouldering BTE - Burnt to extremities





1066

EC – Escalating combustion DNS - Material did not split ME - Manually extinguished DNO – Did not observe time of event

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL. A company registered in England & Wales with company number 04669651. VAT Number GB 816764800. BTTG® and Shirley® are trade names of Shirley Technologies Ltd. The supply of all goods and services is subject to our standard terms of business, copies of which are available on request. Our laboratories are accredited to EN ISO/IEC 17025.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

21 March 2024 Date:

Our Ref: 23/61895/03/24 Your Ref: 83A26448

> 5 of 5 Page:

Client: **Camira Fabrics Ltd**

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010:Part 8.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

Uncertainty Budget

Measurements: ±2mm Timings: ±2 seconds.

...... R Walls, Laboratory Technician Reported by:.....

.... B Bland, Technical Customer Service Officer Countersigned by:....

Enquiries concerning this report should be addressed to Customer Services.



