

Our Ref: SW/SW

6 November 2024

**Report 428293**
**Page: 1 of 3**

Camira Fabrics Limited  
Meltham Mills  
Meltham  
United Kingdom  
West Yorkshire  
HD9 4AY

Contact: Luke Russell;Amanda Jack

DATE RECEIVED : 29 OCT 2024  
QUALITY/REFERENCE : INTERVENE TEXTURE  
REPUTED FIBRE CONTENT : NOT GIVEN  
FABRIC DESCRIPTION : WOVEN  
COLOUR/DESIGN : HYH100  
STYLE NUMBER : 541566  
ORDER NUMBER : 83A29818

PERFORMANCE STANDARD : GENERAL

TEST PERFORMANCE DATE(S) : 29/10/2024 - 06/11/2024


**REPORT SUMMARY**

Tests	Method	Pass	Fail	Requirement
Resistance to abrasion	BS EN ISO 12947-2:2016 Abrasion			No requirement

Eurofins MTS Consumer Product Testing UK Ltd  
118 Lupton Avenue, Leeds, West Yorkshire, LS9 6ED  
Tel: 0113 248 8830 Email: info@hstts.co.uk  
Registered No. 7337435 VAT No. 887127683

6 November 2024

**Report 428293****Page: 2 of 3****S. WISEMAN**  
**LABORATORY DIRECTOR**

*This report may not be reproduced except in full without the written approval of Eurofins MTS Consumer Product Testing Services Limited. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.*

Eurofins MTS Consumer Product Testing UK Ltd  
118 Lupton Avenue, Leeds, West Yorkshire, LS9 6ED  
Tel: 0113 248 8830 Email: [info@hstts.co.uk](mailto:info@hstts.co.uk)  
Registered No. 7337435 VAT No. 887127683

6 November 2024

**Report 428293****Page: 3 of 3****PHYSICAL****BS EN ISO 12947-2:2016 Abrasion**

12 kPa load.

Requirement:

No requirement

Number of rubs to breakdown:
Head 1 100,000+
Head 2 100,000+
Head 3 100,000+
Head 4 100,000+