

Confidential Report

Our Ref: 23/58694/07/21





Client:

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

: www.bttg.co.uk

Date: 13 July 2021

Our Ref: 23/58694/07/21

Your Ref: ---

Page: 1 of 6

Camira Fabrics Ltd

The Watermill Wheatley Park Mirfield West Yorkshire WF14 8HE

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: 83A12425

Date of Receipt: 02 July 2021

Date Test Started: 12 July 2021

Description of Sample: One sample of fabric, which was referenced by the client as;

Quest + EnviroFlam 5, Batch: 473905 D1234B, Colour: Grey

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 8

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

Note: This report relates only to the samples submitted and as described in the report.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.

A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : www.bttg.co.uk

Date: 13 July 2021

Our Ref: 23/58694/07/21

Your Ref: ---

Page: 2 of 6

Client: Camira Fabrics Ltd

Product Description

Company Name	Camira Fabrics	
FABRIC		
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	Upholsery Fabric	
Name and/or Identification of the Product Tested	Quest + EnviroFlam 5	
Materials of the Product and its Composite Ratio (i)	100% Post-Consumer Recycled Polyester inc. 75% SEQUAL Yarn	
Composition of Weave (ii)	Hopsack	
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	IP	
Yarn Number Count	IP	
Thickness (mm)	0.77 (Nominal)	
Mass per Unit Area (g/m²)	330 g/m2 (Nominal)	
Colour and Tone (iii)	Grey	
Method and Quantity of Fire Retardant Treatment	EnviroFlam 5 (Backcoat)	

- (i) Such as wool, nylon, polyester, etc.
- (ii) Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : www.bttg.co.uk

Date: 13 July 2021

Our Ref: 23/58694/07/21

Your Ref: ---

Page: 3 of 6

Client: Camira Fabrics Ltd

Testing to IMO FTP Code 2010: Part 8

Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 23±2°C temperature and 50±5% relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m³ and 21°C.

Procedure

The samples was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22kg/m³.

Requirements

Ignition Source 0 No progressive smouldering or flaming within 1 hour of the placement of the cigarette.

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm) 68mm x 80mm

Mass (g) 0.92 Smouldering Rate (mins/secs) 11m, 12s





Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk : www.bttg.co.uk

Date: 13 July 2021

Our Ref: 23/58694/07/21 Your Ref: ---

Page: 4 of 6

Client: Camira Fabrics Ltd

Results

Cigarette Test - Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	DNP	DNP
Time of cover split	DNS	DNS
Melting (Yes/No)	Yes	Yes
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Observations	DNP, DNS	DNP, DNS
Pass/Fail	PASS	PASS

Result of the Cigarette Test: Pass

Propane Flame Test – Source 1

Specimen No.	1	2
Time of Ignition (s)	4	4
Extinction time of flames after removal of burner (s)	1	2
Time to Cover Split (s)	DNS	DNS
Melting (Yes/No)	Yes	Yes
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Observations:	DNS	DNS
Pass/Fail	PASS	PASS

Result of the Flame Test: Pass

Acronym

DNP – Did not propagate ES – Escalating smouldering BTE – Burnt to extremities





EC – Escalating combustion DNS – Material did not split

ME – Manually extinguished DNO – Did not observe time of event



Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 13 July 2021

Our Ref: 23/58694/07/21

Your Ref: ---

Page: 5 of 6

Client: Camira Fabrics Ltd

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010:Part 8.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by: B Bland, Technical Customer Services Officer

Countersigned by:..... P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 13 July 2021

Our Ref: 23/58694/07/21

Your Ref: ---

Page: 6 of 6

Client: Camira Fabrics Ltd

Uncertainty Budget - Annex

The overall uncertainty budget IMO FTP Code 2010:Part 8 is as follows:-

Measurements: ±1mm
Timings: ±2 seconds

