

Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 01 December 2020

 Our Ref:
 23/58015-2

 Your Ref:
 83A09560

Page: 1 of 6

Client: Camira Fabrics Limited

The Watermill Wheatley Park Mirfield WF14 8HE

Job Title: Fire test on one sample of fabric

Client's Order No: 83A09560

Date of Receipt: 20 November 2020 Date of Test Start: 30 November 2020

Description of Sample(s): One sample of fabric identified as follows was received for testing:

Blazer, Bromsgrove, Run 447362

Work Requested: We were asked to make the following test:

IMO FTP Code 2010 Part 8 (Upholstered Furniture)





Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 01 December 2020

 Our Ref:
 23/58015-2

 Your Ref:
 83A09560

Page: 2 of 6

Camira Fabrics Limited

Sample was identified as follows:

Blazer, Bromsgrove, Run 447362

Testing to IMO FTP Code 2010: Part 8 – Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 23±2°C temperature and 50±5% relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m³ and 16°C.

Procedure

The samples was tested in accordance with IMO FTP Code 2010: Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22 kg/m³.

Requirements

Ignition Source 0 No progressive smouldering or flaming within 1 hour of the placement of the cigarette

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner

tube

Cigarette Specification (Source 0)

Dimensions (mm) 68mm x 8mm

Mass (g) 0.92 Smouldering Rate (mins/secs) 10.29





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 01 December 2020

 Our Ref:
 23/58015-2

 Your Ref:
 83A09560

Page: 3 of 6

Camira Fabrics Limited

Product Description

Company Name	Camira Fabrics	
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	All	
Name and/or Identification of the Product Tested	Blazer	
Materials of the Product and its Composite Ratio (i)	100% Virgin Wool	
Composition of Weave (ii)	Plain	
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Not specified by client	
Yarn Number Count	Not specified by client	
Thickness (mm)	1.7 mm	
Mass per Unit Area (g/mm²)	460 g/m2 644 g/lin.m	
Colour and Tone (iii)	Bromsgrove Run 447362	
Method and Quantity of Fire Retardant Treatment	Not supplied by client	

- (i) Such as wool, nylon, polyester, etc.
- (ii) Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 01 December 2020

 Our Ref:
 23/58015-2

 Your Ref:
 83A09560

Page: 4 of 6

Camira Fabrics Limited

RESULTS

Sample Ref: Blazer, Bromsgrove, Run 447362

Cigarette Test - Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	29	31
Time of cover split	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Pass/Fail	PASS	PASS

Result of the Cigarette Test: PASS

Propane Flame Test - Source 1

Specimen No.	1	2
Time of Ignition (s)	7	5
Extinction time of flames after removal of burner (s)	1	1
Time to Cover Split (s)	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Pass/Fail	PASS	PASS

Result of the Flame Test: PASS

Acronym

DNP – Did not propagate
ME – Manually extinguished
DNS – Material did not split
BTE – Burnt to extremities

EC – Escalating combustion ES – Escalating smouldering

DNO – Did not observe time of event





Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 01 December 2020

 Our Ref:
 23/58015-2

 Your Ref:
 83A09560

Page: 5 of 6

Camira Fabrics Limited

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010, Part 8.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by:

Laboratory Technician

Countersigned By:.....

P Doherty Manager

Enquiries concerning this report should be addressed to Customer Services





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 01 December 2020

 Our Ref:
 23/58015-2

 Your Ref:
 83A09560

Page: 6 of 6

Camira Fabrics Limited

Uncertainty Budget – Annex

The overall uncertainty budget IMO FTP Code 2010 : Part 8 is as follows:

Measurements: ±1mm Timings: ±2 seconds

