



Confidential Report

Our Ref: 23/60264/10/22





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 19 October 2022

Our Ref: 23/60264/10/22

Your Ref: ---

Page: 1 of 5

Client:

Camira Fabrics Ltd

The Watermill
Wheatley Park
Mirfield
West Yorkshire
WF14 8HE

Job Title:

Fire Test on One Fabric Sample

Clients Order Ref:

83A19476

Date of Receipt:

14 October 2022

Date Test Started:

19 October 2022

Description of Sample:

One sample of fabric, which was referenced by the client as;

Q217, Batch: 509183, Colour: Blocks V0107E

Work Requested:

We were asked to make the following fire test:

IMO FTP Code 2010:Part 8

* subcontracted test, UKAS accredited
** subcontracted test, EN ISO/IEC 17025 accredited
*** not UKAS accredited

Note: This report relates only to the items tested.



Date: 19 October 2022

Our Ref: 23/60264/10/22
Your Ref: ---

Page: 2 of 5

Client:

Camira Fabrics Ltd

Product Description

Company Name	Camira Fabrics
FABRIC	
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	Upholstery Fabric
Name and/or Identification of the Product Tested	Q217
Materials of the Product and its Composite Ratio (i)	100% Virgin Wool
Composition of Weave (ii)	Plain Weave
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	IP
Yarn Number Count	IP
Thickness (mm)	1.7 (Nominal)
Mass per Unit Area (g/m ²)	410 g/m² (Nominal)
Colour and Tone (iii)	Blocks V0107E
Method and Quantity of Fire Retardant Treatment	N/A
FILLINGS	
Material (Name of Manufacturer, Type Designation)	--
Type of Filling Material (eg. Foam, Polyester Fibre etc.)	--
Weight per Unit Volume (kg/m ³)	--
Method and Quantity of Fire Retardant Treatment	--

- (i) Such as wool, nylon, polyester, etc.
(ii) Such as plain, weave, twilled.
(iii) If the product has a pattern, the representative colour shall be described.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 19 October 2022

Our Ref: 23/60264/10/22
Your Ref: ---

Page: 3 of 5

Client: Camira Fabrics Ltd

Testing to IMO FTP Code 2010 : Part 8 Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of $23\pm 2^{\circ}\text{C}$ temperature and $50\pm 5\%$ relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m^3 and 21°C .

Procedure

The samples was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately $20\text{-}22\text{kg/m}^3$.

Requirements

Ignition Source 0 No progressive smouldering or flaming within 1 hour of the placement of the cigarette.

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm)	69mm x 8.0mm
Mass (g)	0.84
Smouldering Rate (mins/secs)	10m 02s



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.

Date: 19 October 2022

Our Ref: 23/60264/10/22
Your Ref: ---

Page: 4 of 5

Client: Camira Fabrics Ltd

Results

Cigarette Test – Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	DNP	DNP
Time of cover split	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Observations	DNP/DNS	DNP/DNS
Pass/Fail	PASS	PASS

Result of the Cigarette Test: Pass

Propane Flame Test – Source 1

Specimen No.	1	2
Time of Ignition (s)	5	5
Extinction time of flames after removal of burner (s)	1	13
Time to Cover Split (s)	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Observations:	DNS	DNS
Pass/Fail	PASS	PASS

Result of the Flame Test: Pass

Acronym

DNP – Did not propagate
ES – Escalating smouldering
BTE – Burnt to extremities

EC – Escalating combustion
DNS – Material did not split

ME – Manually extinguished
DNO – Did not observe time of event





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 19 October 2022

Our Ref: 23/60264/10/22
Your Ref: ---

Page: 5 of 5

Client: Camira Fabrics Ltd

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010:Part 8.


Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<http://www.bttg.co.uk/decision-rules-policy>) for further information.

Uncertainty Budget

Measurements: $\pm 2\text{mm}$
Timings: ± 2 seconds.

Reported by:  B Bland, Technical Customer Services Officer

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2022 Shirley Technologies Limited. All rights reserved.