

## FLAMMABILITY TEST CERTIFICATE - 74298

**COMPANY DETAILS:** CAMIRA FABRICS  
THE WATERMILL, WHEATLEY PARK, MIRFEILD  
WEST YORKSHIRE, WF14 8HE

**CONTACT NAME(S):** GRETA ZIAUGRAITE  
**TEL:** 0192 481368  
**EMAIL:** [greta.ziaugraite@camirafabrics.com](mailto:greta.ziaugraite@camirafabrics.com)

**DATE RECEIVED:** 05/04/2019  
**DATE TESTED:** 10/04/2019  
**DATE ISSUED:** 10/04/2019  
**PO NUMBER:** 83A03503

**SAMPLE DESCRIPTION:** REGENT (BRITISH VELVET COLORADO)  
**COLOUR:** WHITE  
**QUALITY/BATCH REF:** REGENT (BRITISH VELVET COLORADO)  
**COMPOSITION:** 100% POLYESTER  
**MODEL NO:** DEV NO; D8048  
**SAMPLE END USE:** CONTRACT  
**MANUFACTURER:** BRITISH VELVET  
**SUPPLIER/BUYER:** NOT STATED

### PERFORMANCE REQUIRMENT:

BS 5867-2: 2008 Type B – Flammability requirements specification – Fabrics for curtains, drapes and window blinds.

### TEST METHOD:

BS EN ISO 15025: 2002 Procedure A (Surface Ignition) – Protective clothing – Protection against heat and flame.  
Methods of test for limited flame spread.

### PRE-TREATMENT:

The sample had been tested without any cleansing procedure.

### CONDITIONING:

The sample was conditioned for at least 24 hrs in a specified atmosphere at  $20 \pm 2^{\circ}\text{C}$  and  $65 \pm 5\%$  r h.

Authorised By:



Zeb Alam  
Operations Director

Mark Jones  
Quality Manager

Karen Brooks  
Managing Director

## FLAMMABILITY TEST CERTIFICATE - 74298

### TEST RESULTS:

#### BEFORE CLEANISNG:

Test Criteria	1	2	3	4	5	6
Specimen Direction:	↑	↓	↑	←	→	←
Application Time:	15	15	15	15	15	15
Hole formed: (Y/N)	YES	YES	YES	YES	YES	YES
Hole reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flame reached the edge: (Y/N)	NO	NO	NO	NO	NO	NO
Flaming Debris: (Y/N)	NO	NO	NO	NO	NO	NO
Damage Length: (mm)	50	51	47	49	48	53
Damage width: (mm)	22	23	22	22	23	22
<b>Test Result</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>	<b>PASS</b>

#### PASS/FAIL CRITERIA:

No Part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of the sample. If any part of any hole or any part of the lowest boundary of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens must be tested and comply with the above requirements, the fabric shall be deemed to conform to the requirements of type B of BS 5867-2

#### CONCLUSION:

The sample supplied **meets** the type B performance requirement of BS 5867-2: 2008 when tested in accordance with BS EN ISO 15025: 2002 Procedure A (Surface Ignition) before cleansing.

END OF REPORT